

# Links between shell chemistry and microstructure

## A case study using *Arctica islandica*

**Ellen Schnabel<sup>1</sup>**

Kotaro Shirai<sup>2</sup>, Naoko Murakami-Sugihara<sup>2</sup>, Klaus Peter Jochum<sup>3</sup>, Nils Höche<sup>1</sup>, Kozue Nishida<sup>4</sup>, and Bernd R. Schöne<sup>1</sup>

<sup>1</sup>Institute of Geosciences, University of Mainz, Johann-Joachim-Becher-Weg 21, 55128 Mainz, Germany


<sup>2</sup>Atmosphere and Ocean Research Institute, The University of Tokyo, 5-1-5, Kashiwanoha, Kashiwa-shi, Chiba 277-8564 Japan

<sup>3</sup>Max Planck Institute for Chemistry, Hahn-Meitner-Weg 1, 55128 Mainz, Germany

<sup>4</sup>National Institute of Technology, Ibaraki College; 866 Nakane, Hitachinaka-shi, Ibaraki-ken 312-8508 Japan





# Bivalve cross section



# Element/Ca ratios in different specimens

In contemporaneous shell portions of specimen from the same site, Sr/Ca ratios can vastly differ from each other (more than 30% in the ventral margin).

Na/Ca ratios show less variation among specimen (below 1% in the ventral margin)





The plotted values are arithmetic means of all values measured in one annual increment with one standard deviation.

# Element/Ca ratios in hinge and ventral margin


Within the same specimen, isochronous shell portions of the hinge plate and the ventral margin show nearly identical Sr/Ca ratios.

For all specimen, Ba/Ca, B/Ca and Na/Ca tend to be larger in the hinge.



The plotted values are arithmetic means of all values measured in one annual increment with one standard deviation.

# Element/Ca variations within the hinge plate







The pictures show relative element-to-calcium ratios in the hinge plate measured by LA-ICP-MS. Light color indicates high ratios. Within isochronous portions, the highest values occur on the axis of maximum growth. The element-to-calcium ratios gradually decrease in slower growing shell portions.




# Microstructure




homogeneous  
microstructure




Crossed acicular  
microstructure



Growth line  
irregular simple  
prisms





# Si/Ca & Na/Ca variations within the ventral margin




The diagrams show the Si/Ca and the Na/Ca ratios of specimen 202 in different regions of the ventral margin.

Si/Ca is significantly higher in the outer portion of the shell layer, whereas Na/Ca is lower.



# Links between chemistry and microstructure



From the inner to the outer part of the outer portion of the outer shell layer, the microstructure of *Arctica islandica* in the ventral margin gradually changes from crossed-acicular to homogeneous. The element chemistry of the shells was exclusively measured (by LA-ICP-MS) in shell portions consisting of homogeneous microstructure. Nevertheless, there are visible differences between the biomineral units concerning shape, size and preferential orientation.

Along with the microstructure changes, element-to-calcium ratios, like Si/Ca or Na/Ca, change as well. This suggests that these phenomena are linked.

Work in progress:  
Identification and quantification of relevant microstructural parameters

